



ABS-M30

PRODUCTION-GRADE THERMOPLASTIC FOR FDM 3D PRINTERS

ABS-M30™ is up to 25 to 70 percent stronger than standard ABS and is an ideal material for conceptual modeling, functional prototyping, manufacturing tools and production parts. ABS-M30 has greater tensile, impact and flexural strength than standard ABS. Layer bonding is significantly stronger than that of standard ABS, for a more durable part. This results in more realistic functional tests and higher quality parts for end use. ABS-M30 parts are stronger, smoother and have better feature detail. ABS-M30 runs the Xtend 500 Fortus Plus option, which enables more than 400 hours of unattended build time.

MECHANICAL PROPERTIES ¹	TEST METHOD	ENGLISH		METRIC	
		XZ Axis	ZX Axis	XZ Axis	ZX Axis
Tensile Strength, Yield (Type 1, 0.125", 0.2"/min)	ASTM D638	4,550 psi	3,750 psi	31 MPa	26 MPa
Tensile Strength, Ultimate (Type 1, 0.125", 0.2"/min)	ASTM D638	4,650 psi	4,050 psi	32 MPa	28 MPa
Tensile Modulus (Type 1, 0.125", 0.2"/min)	ASTM D638	320,000 psi	310,000 psi	2,230 MPa	2,180 MPa
Tensile Elongation at Break (Type 1, 0.125", 0.2"/min)	ASTM D638	7%	2%	7%	2%
Tensile Elongation at Yield (Type 1, 0.125", 0.2"/min)	ASTM D638	2%	1%	2%	1%
Flexural Strength (Method 1, 0.05"/min)	ASTM D790	8,700 psi	7,000 psi	60 MPa	48 MPa
Flexural Modulus (Method 1, 0.05"/min)	ASTM D790	300,000 psi	250,000 psi	2,060 MPa	1,760 MPa
Flexural Strain at Break (Method 1, 0.05"/min)	ASTM D790	4%	3.5%	4%	3.5%

MECHANICAL PROPERTIES	TEST METHOD	ENGLISH	METRIC
		XZ Axis	XZ Axis
IZOD Impact, notched (Method A, 23°C)	ASTM D256	2.4 ft-lb/in	128 J/m
IZOD Impact, un-notched (Method A, 23°C)	ASTM D256	5.6 ft-lb/in	300 J/m



THERMAL PROPERTIES ²	TEST METHOD	ENGLISH	METRIC
Heat Deflection (HDT) @ 66 psi, 0.125" unannealed	ASTM D648	204°F	96°C
Heat Deflection (HDT) @ 264 psi, 0.125" unannealed	ASTM D648	180°F	82°C
Vicat Softening Temperature (Rate B/50)	ASTM D1525	210°F	99°C
Glass Transition (Tg)	DMA (SSYS)	226°F	108°C
Coefficient of Thermal Expansion (flow)	ASTM E831	4.90x10 ⁻⁰⁵ in/in/°F	8.82x10 ⁻⁰⁵ mm/mm/°C
Coefficient of Thermal Expansion (xflow)	ASTM E831	4.70x10 ⁻⁰⁵ in/in/°F	8.46x10 ⁻⁰⁵ mm/mm/°C
Melting Point	-----	Not Applicable ²	Not Applicable ²

STRATASYS.COM



ABS-M30

PRODUCTION-GRADE THERMOPLASTIC FOR FDM 3D PRINTERS

At the core:

Advanced FDM Technology

FDM® (fused deposition modeling) technology works with engineering-grade thermoplastics to build strong, long-lasting and dimensionally stable parts with the best accuracy and repeatability of any 3D printing technology. These parts are tough enough to be used as advanced conceptual models, functional prototypes, manufacturing tools and production parts.

Meet production demands

FDM systems are as versatile and durable as the parts they produce. Advanced FDM 3D Printers boast the largest build envelopes and material capacities in their class, delivering longer, uninterrupted build times, bigger parts and higher quantities than other additive manufacturing systems, delivering high throughput, duty cycles and utilization rates.

Opening the way for new possibilities

FDM 3D Printers streamline processes from design through manufacturing, reducing costs and eliminating traditional barriers along the way. Industries can cut lead times and costs, products turn out better and get to market faster.

No special facilities needed

FDM 3D Printers are easy to operate and maintain compared to other additive fabrication systems because there are no messy powders or resins to handle and contain, and no special venting is required because FDM systems don't produce noxious fumes, chemicals or waste.

ELECTRICAL PROPERTIES ³	TEST METHOD	ORIENTATION	VALUE RANGE
Volume Resistivity	ASTM D257	XZ Axis	4.0x10 ¹⁵ - 3.3x10 ¹⁶ ohm-cm
Dielectric Constant	ASTM D150-98	XZ Axis	2.6 - 2.86
Dissipation Factor	ASTM D150-98	XZ Axis	0.0048 - 0.0054
Dielectric Strength	ASTM D149-09, Method A	XY Axis	100 V/mil
Dielectric Strength	ASTM D149-09, Method A	XZ Axis	360 V/mil

OTHER ¹	TEST METHOD	VALUE
Specific Gravity	ASTM D792	1.04
Rockwell Hardness	ASTM D785	109.5

SYSTEM AVAILABILITY	LAYER THICKNESS CAPABILITY	SUPPORT STRUCTURE	AVAILABLE COLORS
Fortus 380mc™	0.013 inch (0.330 mm)	Soluble Supports	<input type="checkbox"/> Ivory <input type="checkbox"/> White <input checked="" type="checkbox"/> Black <input checked="" type="checkbox"/> Dark Grey <input checked="" type="checkbox"/> Red <input checked="" type="checkbox"/> Blue
Fortus 450mc™	0.010 inch (0.254 mm)		
Fortus 900mc™	0.007 inch (0.178 mm)		
Stratasys F123™ Series	0.005 inch (0.127 mm) ⁴		

The information presented are typical values intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. End-use material performance can be impacted (+/-) by, but not limited to, part design, end-use conditions, test conditions, etc. Actual values will vary with build conditions. Tested parts were built on Fortus 400mc™ @ 0.010" (0.254 mm) slice. Product specifications are subject to change without notice.

The performance characteristics of these materials may vary according to application, operating conditions or end use. Each user is responsible for determining that the Stratasys material is safe, lawful and technically suitable for the intended application, as well as for identifying the proper disposal (or recycling) method consistent with applicable environmental laws and regulations. Stratasys makes no warranties of any kind, express or implied, including, but not limited to, the warranties of merchantability, fitness for a particular use, or warranty against patent infringement.

¹Literature value unless otherwise noted.


²Due to amorphous nature, material does not display a melting point.

³All Electrical Property values were generated from the average of test plaques built with default part density (solid). Test plaques were 4.0 x 4.0 x 0.1 inches (102 x 102 x 2.5 mm) and were built both in the flat and vertical orientation. The range of values is mostly the result of the difference in properties of test plaques built in the flat vs. vertical orientation.

⁴0.005 inch (0.127 mm) layer thickness not available for Fortus 900mc.

Colors: The test data was collected using ABS-M30 Ivory (natural) specimens. ABS-M30 colored material will have similar properties, but can vary by up to 10%. Orientation: See Stratasys Testing white paper for more detailed description of build orientations.

- XZ = X or "on edge"
- XY = Y or "flat"
- ZX = or "upright"



STRATASYS.COM
ISO 9001:2008 Certified

HEADQUARTERS

7665 Commerce Way, Eden Prairie, MN 55344
+1 888 480-3548 (US Toll Free)
+1 952 937-3000 (Intl)
+1 952 937-0070 (Fax)

1 Holtzman St., Science Park, PO Box 2496
Rehovot 76124, Israel
+972 74 745-4000
+972 74 745-5000 (Fax)