

General Purpose Resins

Materials for High Resolution Models and Rapid Prototyping

High Detail. For demanding applications, our carefully-engineered resins capture the finest features in your model.

Strong and Precise. Our resins create accurate and robust parts, ideal for rapid prototyping, functional testing and product development.

Smooth Surface Finish. Perfectly smooth right out of the printer, parts printed on the Formlabs stereolithography printers have the polish and finish of a final product.



V4 Clear
FLGPCL04

V4 Grey
FLGPGR04

V2 Draft
FLDRGR02

V1 Grey Pro
FLPRGR01

V4 White
LGPWH04

V4 Black
FLGPBL04

V4 Color
FLGPCB01

* May not be available in
all regions

MATERIAL PROPERTIES DATA

Standard Resins

The following material properties are comparable for Clear Resin, White Resin, Grey Resin, Black Resin, and Color Kit.

	METRIC ¹		IMPERIAL ¹		METHOD
	Green ²	Post-Cured ³	Green ²	Post-Cured ³	
Tensile Properties					
Ultimate Tensile Strength	38 MPa	65 MPa	5510 psi	9380 psi	ASTM D638-14
Tensile Modulus	1.6 GPa	2.8 GPa	234 ksi	402 ksi	ASTM D638-14
Elongation at Break	12%	6%	12%	6%	ASTM D638-14
Flexural Properties					
Flexural Modulus	1.3 GPa	2.2 GPa	181 psi	320 psi	ASTM D 790-15
Impact Properties					
Notched Izod	16 J/m	25 J/m	0.3 ft-lbf/in	0.46 ft-lbf/in	ASTM D256-10
Thermal Properties					
Heat Deflection Temp. @ 1.8 MPa	43 °C	58 °C	109 °F	137 °F	ASTM D 648-16
Heat Deflection Temp. @ 0.45 MPa	50 °C	73 °C	121 °F	134 °F	ASTM D 648-16

¹ Material properties can vary with part geometry, print orientation, print settings, and temperature.

² Data was obtained from green parts, printed using Form 2, 100 µm, Clear settings, without additional treatments.

³ Data was obtained from parts printed using Form 2, 100 µm, Clear settings and post-cured with 1.25 mW/cm² of 405 nm LED light for 60 minutes at 60 °C.

SOLVENT COMPATIBILITY

Percent weight gain over 24 hours for a printed and post-cured 1 x 1 x 1 cm cube immersed in respective solvent:

Solvent	24 hr weight gain, %	Solvent	24 hr weight gain, %
Acetic Acid 5%	< 1	Mineral oil (Light)	< 1
Acetone	Sample cracked	Mineral oil (Heavy)	< 1
Bleach ~5% NaOCl	< 1	Salt Water (3.5% NaCl)	< 1
Butyl Acetate	< 1	Skydrol 5	1
Diesel Fuel	< 1	Sodium Hydroxide solution (0.025% PH 10)	< 1
Diethyl glycol Monomethyl Ether	1.7	Strong Acid (HCl conc)	Distorted
Hydraulic Oil	< 1	Water	< 1
Hydrogen peroxide (3%)	< 1	Xylene	< 1
Isooctane (aka gasoline)	< 1		
Isopropyl Alcohol	< 1		