

POLYMER SOLUTIONS

PA 3200 GF

Material Data Sheet

PA 3200 GF

Product Description

PA 3200 GF is a white polyamide 12 powder filled with glass beads (40 wt%). Parts made from PA 3200 GF show high rigidity while maintaining a good elongation at break. In addition, they are characterized in particular by their special wear resistance, which makes them a perfect fit for increased abrasion resistance requirements.

MAIN CHARACTERISTICS

- High stiffness
- Wear resistance
- Improved temperature performance

TYPICAL APPLICATIONS

- Machine components that require enhanced siffness under load, e.g., housings
- Heavily used parts that require enhanced wear and abrasion resistance
- Forming tools

MECHANICAL PROPERTIES	DRY / CONDITIONED	UNIT	TEST STANDARD
Tensile Modulus			ISO 527-1/-2
X Orientation	3200 / -	MPa	
Y Orientation	3200 / -	MPa	
Z Orientation	2500 / -	MPa	
Tensile Strength			ISO 527-1/-2
X Orientation	51 / -	MPa	
Y Orientation	51 / -	MPa	
Z Orientation	47 / -	MPa	
Strain at Break			ISO 527-1/-2
X Orientation	9 / -	%	
Y Orientation	9 / -	%	
Z Orientation	5.5 / -	%	
Flexural Modulus			ISO 178
X Orientation	2900 / -	MPa	
Flexural Strength			ISO 178
X Orientation	73 / -	-	
Charpy Impact Strength (+23°C)			ISO 179
X Orientation	35 / -	kJ/m²	
Charpy Notched Impact Strength (+23°C)			ISO 179
X Orientation	5.4 / -	kJ/m²	
Izod Impact Strength (+23°C)			ISO 179
X Orientation	21 / -	kJ/m²	
Izod Notched Impact Strength (+23°C)			ISO 179
X Orientation	4.2 / -	kJ/m²	
Ball Indentation Hardness			ISO 2039-1
X Orientation	98 / -	MPa	
Shore D Hardness			ISO 7619-1
X Orientation	80 / -	-	

THERMAL PROPERTIES	DRY / CONDITIONED	UNIT	TEST STANDARD
Melting Temperature	-	°C	ISO 11357-1/-3
Temperature of Deflection under Load 1.80 MPa			ISO 75-1/-2
X Orientation	96	°C	
Temperature of Deflection under Load 0.45 MPa			ISO 75-1/-2
X Orientation	157	°C	

OTHER PROPERTIES	VALUE	UNIT	TEST STANDARD
Density	1.22	g/cm³	EOS Method
Powder Color	whitish	-	-
Components Color	whitish	-	-

English ›

HEADQUARTERS

EOS GmbH
Electro Optical Systems

Robert-Stirling-Ring 1
82152 Krailling / Munich
Germany

Tel.: +49 89 893 36-0
Email: info@eos.info
URL: www.eos.info

This powder has not been developed, tested or certified as a medical device according to Directive 93/42/EEC (MDD) or Regulation (EU) 2017/745 (MDR) and is not intended to be used as a medical device, in particular for the purposes specified in Art. 2 No. 1 MDR. Insofar as you intend to use the powder as raw material for the manufacture of pharmaceutical products or medical devices (e.g. as raw material which as a material must meet the requirements of Annex 1, Chapter II MDR), the responsibility and liability for all analyses, tests, evaluations, procedures, risk assessments, conformity assessments, approval and certification procedures as well as for all other official and regulatory measures required for this purpose shall lie solely with you both with regard to the pharmaceutical product and/or medical device manufactured by you and with regard to the properties, suitability, testing, evaluation, risk assessment, other requirements for use of the powder as raw material. In this respect, the limitations of liability pursuant to our General Terms and Conditions and the system sales or material contracts shall apply.

Part properties are provided for information purposes only and EOS makes no representation or warranty, and disclaims any liability, with respect to actual part properties achieved. Part properties are dependent on a variety of influencing factors and therefore, actual part properties achieved by the user may deviate from the information stated herein. This document does not on its own represent a sufficient basis for any part design, neither does it provide any agreement or guarantee about the specific properties of a material or part or the suitability of a material or a part for a specific application.

The achievement of certain part properties as well as the assessment of the suitability of this material for a specific purpose is the sole responsibility of the user. Any information given herein is subject to change without notice.

Status as of 08.11.2026. Subject to technical modifications. EOS is certified according to ISO 9001.
EOS®, Additive Minds® Alumide®, AMQ®, CarbonMide®, DirectMetal®, DMLS®, EOSAME®, EOSINT®, EOSIZE®, EOSPACE®, EOSPRINT®, EOSTATE®, EOSTYLE®, FORMIGA®, LaserProFusion®, PA 2200®, PrimeCast® and PrimePart® are registered trademarks of EOS GmbH Electro Optical Systems in some countries. For more information visit www.eos.info/trademarks.

English ›